

## TECHNICAL SHEET

|                         |   |
|-------------------------|---|
| <b>BRAND</b>            | <b>CERAMICAS APARICI, S.A.</b><br>Ctra. Castellón - Alcora, km 12<br>12130 San Juan de Moró (Castellón) SPAIN   |
| <b>PRODUCT</b>          | <b>NAME: LIENZO GREY ORNATO</b><br><b>FORMAT (cm): 31,6X95,3</b><br><b>BATCH : 20/01/20</b>   |
| <b>TYPE OF PRODUCT</b>  | <b>TYPE:</b> Dry-pressed ceramic tiles, with water absorption $E_b > 10\%$ <b>TYPE RED BODY</b><br><b>USE:</b> For internal and external walls.<br><b>GROUP:</b> BIII |
| <b>REFERENCED RULES</b> | <b>ISO-13006:2012 and UNE EN 14411:2013</b>   |

| Characteristics  | Test Method    | Requirements  | Values Compliance |
|--|----------------|---|-------------------|
| <b>A) DIMENSIONS AND SURFACE QUALITY</b>   |                |   |                   |
| <b>Length and width</b>  |                |   |                   |
| The work size shall be chosen as follows for:  |                |   |                   |
| a) modular tiles:  | EN ISO 10545-2 | In order to allow a nominal joint width of between 2 and 5 mm<br>So that the difference between the work size and the nominal size is not more than 2% (maximum 5 mm) | PASS              |
| b) non-modular tiles:  | EN ISO 10545-2 |   | PASS              |
| The permissible deviation of the average size for each tile (2 or 4 sides) from the work size (W)<br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$ | EN ISO 10545-2 | $\pm 0,75\text{ mm}$<br>$\pm 2,0\text{ mm ó } \pm 0,5\%$  | PASS              |

|  |                |   |                |
|--|----------------|---|----------------|
| <b>Thickness</b>   |                | Declared thickness  | <b>SEE BOX</b> |
| a) The thickness shall be specified<br><br>b) The permissible deviation, of the average thickness of each tile from the work size thickness<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$ | EN ISO 10545-2 | $\pm 0,5 \text{ mm}$<br>$\pm 0,5 \text{ mm ó } \pm 10\%$  | <b>PASS</b>    |
| <b>Straightness of sides (facial sides)</b>  |                |   |                |
| The maximum permissible deviation from straightness, related to the corresponding work sizes.<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $\pm 0,5 \text{ mm}$<br>$\pm 1,5 \text{ mm ó } \pm 0,3\%$   | <b>PASS</b>    |
| <b>Rectangularity</b>  |                |   |                |
| The maximum permissible deviation from rectangularity, related to the corresponding work sizes.<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $\pm 0,75 \text{ mm}$<br>$\pm 2,0 \text{ mm ó } \pm 0,5\%$  | <b>PASS</b>    |
| <b>Surface flatness</b>  |                |   |                |
| The maximum permissible deviation from flatness<br><br>a) centre curvature, related to diagonal calculated from the work sizes.<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$             | EN ISO 10545-2 | $+ 0,75 / - 0,50 \text{ mm}$<br>$+ 2,0 / - 1,5 \text{ mm}$<br>$\text{ó } + 0,5\% / - 0,3\%$                                 | <b>PASS</b>    |
| b) edge curvature, related to the corresponding work sizes.<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $+ 0,75 / - 0,50 \text{ mm}$<br>$+ 2,0 / - 1,5 \text{ mm}$<br>$\text{ó } + 0,5\% / - 0,3\%$                                 | <b>PASS</b>    |
| c) warpage, related to diagonal calculated from the work sizes.<br><br>Requirements for nominal size N<br>$7\text{cm} \leq N < 15\text{cm}$<br>$N \geq 15\text{ cm}$   | EN ISO 10545-2 | $\pm 0,75 \text{ mm}$<br>$\pm 2,0 \text{ mm ó } \pm 0,5\%$  | <b>PASS</b>    |
| <b>Surface quality</b>   |                |   |                |
|  | EN ISO 10545-2 | A minimum of 95% of the tiles shall be free from visible defects that would impair the appearance of a major area of tiles. | <b>PASS</b>    |

| <b>B) PHYSICAL PROPERTIES</b>                             |                              |   |   |
|---|------------------------------|---|---|
| <b>Water absorption (in % by mass)</b>                    |                              |   |   |
|   | EN ISO 10545-3               | E <sub>b</sub> > 10%.<br>When the average exceeds 20%, this shall be indicated.<br>Individual minimum value 9%) | <b>PASS</b>                                 |
| <b>Breaking strength, for:</b>                            |                              |   |   |
| a) Thickness ≥ 7,5 mm                                     | EN ISO 10545-4               | Not less than 600 N   | >600 N                                      |
| b) Thickness < 7,5 mm                                     | EN ISO 10545-4               | Not less than 200 N   | >200 N                                      |
| <b>Flexural tensile strength or modulus of rupture</b>    |                              |   |   |
| a) Thickness ≥ 7,5 mm                                     | EN ISO 10545-4               | Minimum 12 N/mm <sup>2</sup>  | <b>PASS</b>                                 |
| b) Thickness < 7,5 mm                                     | EN ISO 10545-4               | Minimum 15 N/mm <sup>2</sup>  | <b>PASS</b>                                 |
| <b>Coefficient of linear thermal expansion</b>            |                              |   |   |
| from ambient temperature to 100° C                        | EN ISO 10545-8               | Declared Value  | <b>5,8-6,1 10<sup>-6</sup>/°C</b>           |
| <b>Thermal shock resistance</b>                           |                              |   |   |
| Internal uses   | EN ISO 10545-9               | Pass according to EN ISO 10545-9  | <b>PASS</b>                                 |
| External uses   |                              |   | <b>NOT PASS</b>                             |
| <b>Crazing resistance</b>                                 |                              |   |   |
| Glazed tiles  | EN ISO 10545-11              | Pass according to EN ISO 10545-11   | <b>PASS</b>                                 |
| <b>Frost resistance</b>                                   |                              |   |   |
| Internal uses   | EN ISO 10545-12              | Pass according to EN ISO 10545-12   | <b>PASS</b>                                 |
| External uses   |                              |   | <b>NOT PASS</b>                             |
| <b>Bond strength/adhesion , for:</b>                      |                              |   |   |
| cementitious adhesives                                    | EN 12004:2007 +A1: 2012, 4.1 | Declared Value  | <b>Type C1<br/>&gt;0.5 N/mm<sup>2</sup></b> |
| <b>Reaction to fire</b>                                   |                              |   |   |
|   |                              | Class A1  | <b>A1</b>                                   |
| <b>C) CHEMICAL PROPERTIES</b>                             |                              |   |   |
| <b>Resistencia a productos químicos</b>                   |                              |   |   |
| Resistance to household chemicals and swimming pool slats | EN ISO 10545-13              | Minimum GB  | <b>GA</b>                                   |
| <b>Resistance to staining, for:</b>                       |                              |   |   |
| Glazed tiles  | EN ISO 10545-14              | Minimum 3   | <b>5</b>                                    |